

LOCTITE ABLESTIK QMI534

August 2018

PRODUCT DESCRIPTION

LOCTITE ABLESTIK QMI534 provides the following product characteristics:

Technology	Bismaleimide Resin
Appearance	White paste
Product Benefits	<ul style="list-style-type: none"> Hydrophobic Stable at high temperatures Void-free bondline Excellent interfacial adhesion strength
Cure	Heat cure
Application	Semiconductor or NCA

LOCTITE ABLESTIK QMI534 is a Fluoropolymer filled non-conductive adhesive for attachment of intergated circuits and components to advanced substrates, including: PBGAs, CSPs, array packages, and stacked die.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Specific Gravity @ 25 °C	1.25
Viscosity @ 25 °C, mPa·s (cP):	
Speed 5 rpm	9,000
Thixotropic Index (0.5/5 rpm)	5.0
Pot Life @ 25 °C, hours	24
Shelf Life @ -40°C, days	365
Flash Point - See SDS	

TYPICAL CURING PERFORMANCE

Recommended Cure Schedule

SkipCure

≥6 seconds @ 240°C

Alternate Cure Schedule

Conventional Oven

15 minutes @ 150°C

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

Physical Properties

Glass Transition Temperature, °C	-35
Coefficient of Thermal Expansion, TMA, ppm/°C:	
Below Tg	87
Above Tg	171
Thermal Conductivity, W/(m-K)	0.4
Alpha Particle Emissions, particles/cm ² /hr	0.0007
Extractable Ionic Content, :	
Sodium (Na+)	≤20
Potassium (K+)	≤20
Chloride (Cl-)	≤20
Fluoride (F-)	≤20
Moisture Absorption, 168 hours @ 85°C/85% RH, wt. %	≤0.35
DMA Modulus @ 25°C	N/mm ² 300 (psi) (43,500)

Electrical Properties

Volume Resistivity, ohm-cm	>10 ¹³
Dielectric Constant @ 25°C, 1 MHz	2.7

TYPICAL PERFORMANCE OF CURED MATERIAL

Miscellaneous

Die Shear Strength @ 25°C:

300 x 300 mm, 1 mm BLT, Si die on Ag-plated 8 Cu LF, kg-f

GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

Directions for use

Dispensing and Bondline Control:

- LOCTITE ABLESTIK QMI534 adhesion is tested using 150 mm X 150 mm die with 1 mm bondline thickness. Since thinner bondlines increase stress and may affect adhesion, please call your nearest Technical service engineer for consultation in cases where bondlines less than 1 mm are desired
- LOCTITE ABLESTIK QMI534 has excellent rheology and flows easily under shear stresses such as those present during die bonding. Therefore, bondforces used with other adhesives which produce a certain bondline thickness, may result in thinner bondlines with LOCTITE ABLESTIK QMI534. Optimization of die bonding parameters is strongly recommended to consistently meet target bondline thicknesses.

STORAGE:

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage : -40 °C

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{psi} \times 145 = \text{N/mm}^2$
 $\text{MPa} = \text{N/mm}^2$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{MPa}\cdot\text{s} = \text{cP}$

Disclaimer**Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling

and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage: [Except as otherwise noted] All trademarks in this document are trademarks and/or registered trademarks of Henkel and its affiliates in the U.S. and elsewhere.

Reference 1